

TECHNICAL DATA SHEET 2220 SERIES REFLECTIVE INSULATION

(Metalized Film / Double Bubble / Metalized Film)



Verified

US-006-10

Edges Available:

Square Edge 1 Tab Quick Seam


2 Tab Quick Seam

1 Tab
2 Tab

Product Description:

rFOIL® Reflective Insulation is a double layer of polyethylene bubbles sandwiched between two highly reflective metalized film surfaces. This product has been specifically designed for insulating commercial and residential building assemblies, reducing the amount of radiant heat transfer.

Adding rFOIL® Reflective Bubble Insulation to your construction project improves the insulation value of the building envelope and significantly increases it's energy efficiency. All products in this line are classified as Class 1 / Class A in accordance with the ASTM-E84 fire test standard. The product was mounted in accordance to ASTM-E2599.



ASTM INTERNATIONAL

RIMA International

Features:

- Class 1 / Class A Fire Rating
- 96% Reflectivity for optimal thermal performance
- Unaffected by moisture & controls condensation

Applications:

- Crawlspace
- Basement Insulation
- Residential Insulation
- Cathedral Ceiling
- Under Metal Roofing - Post Frame Buildings
- Metal Buildings

Radiant barrier and vapor barrier all-in-one
 Double bubble provides an effective thermal break

- Agricultural & Livestock Buildings
- Mini Storage Buildings

Stock Roll Sizes:

| Size: | 48" x 125' | 72" x 125' | 72" x 102' |
|----------|-------------|-------------|-------------|
| Part No. | 2220-48-125 | 2220-72-125 | 2220-72-102 |

Custom sizes available

| PHYSICAL PROPERTIES | TEST | VALUE |
|----------------------------------|-----------------|---|
| NOMINAL THICKNESS | — | 5/16" |
| | ASTM E84-08 | CLASS 1 / CLASS A |
| FIRE RATING | ASTM E84-08 | FLAME SPREAD = 0 / SMOKE DEVELOPED = 20 |
| | CAN/ULC-S102-10 | FLAME SPREAD = 0 / SMOKE DEVELOPED = 10 |
| FIRE RATING - FULL ROOM BURN | NFPA 286 | PASSES |
| EMISSIVITY | ASTM C1371-04A | 0.04 |
| REFLECTIVITY | ASTM E903 | 0.96 |
| WATER VAPOR PERMEABILITY | ASTM E96 | 0.02 Perms |
| RESISTANCE TO FUNGI and BACTERIA | ASTM C1149 | DOES NOT PROMOTE GROWTH |
| PLIABILITY | ASTM C1224-03 | NO CRACKING |
| BLEEDING and DELAMINATION | ASTM C1224-03 | NO BLEEDING or DELAMINATION |
| CORROSIVENESS | ASTM D3310-00 | PASSES |



279 Humberline Drive Etobicoke, ON M9W 5T6 Toll Free: 1-800-837-8961 Local: 416-798-1340 Email: sales@rfoil.com Website: www.rfoil.com Published: April 15, 2022

